

Graphitization Furnace

RDC-201

R&D
Carbon

Granular Electrodes Lining R&D

General Description

To obtain high quality graphite electrodes and cathodes produced from calcined coke, a heat-treatment to a temperature close to 3000°C is mandatory. The aim of this step is to obtain a graphitized structure of the material, essentially to reach very low electrical resistivity levels. At the production scale, breakage of the electrodes could occur, mainly because of their puffing propensity, when the power curve is not optimized by taking into account the length change of the electrodes during the graphitization process. Knowing in advance the electrode behavior by pilot evaluations is necessary.

The graphitization can be conducted with the RDC-201 apparatus, which has the exact same principle as a full-scale lengthwise graphitization furnace. A column of sample core with a diameter of 50 mm and a total length of 470 mm is clamped between two graphite electrodes with a specific pressure. The heat-up rate is automatically controlled by the regulation of the electrical current flowing through the column of samples. Specific heat-up schedules can be defined up to a maximum temperature of 3000°C and a heat-up rate up to approximately 500°C/h. During the entire process, the length change of the column is measured and recorded. In addition, the column can be replaced by a graphite box to graphitize granular carbon samples (approximately 500 g per run depending on the bulk density of the material). After the graphitization step, the materials are ready for the measurement of their properties.

Technical Information

Function	Graphitization
Property	Length change vs temperature curve
Maximum Temperature	3000°C
Sample	Electrode cores Ø 50 x max. 470 mm or ~ 500 g of granular carbon
Process Time	~ 48 hours
Installation	Floor standing
Dimensions (LxWxH)	410 x 370 x 510 cm
Weight	5500 kg
Electrical Property	400 V 3/N/PE, 50 Hz 100 kW, 160 A
Fluid Property	Air : 6-8 bar Argon : 50 l/h, 3-7 bar
Consumable	Low Sulfur Packing Coke (4-1 mm)
Database Connection	No



Additional Recommended Equipment

Core Drilling Machine (RDC-157)
Resiflex (RDC-147)
Saw (RDC-148)
Drying oven (min. temperature 180°C)
Test equipment for analysis